

Solvent-free 2-component wood floor oil, white

MAGIC OIL 2K WHITE

Solvent-free 2-component wood flooring oil with natural oils (Linseed oil/linseed oil alkyd) and waxes, cross-linking and drying by oxidation after addition of hardener

PRODUCT DESCRIPTION:

Oil-wax combination that leaves an open-pored breathable and diffusive surface. Due to the wax content, a uniform matt, velvety surface is produced. Emphasises the structure of the wood with the colour white and underlines a Scandinavian living style.

SUITABLE FOR:

- ▶ sanded wood flooring with filled joints
- ▶ woodblocks
- ▶ use on wood floors installed over warm water underfloor heating systems



PRODUCT BENEFITS / PROPERTIES:

- ▶ very high resistance to mechanical and chemical wear
- ▶ enhances the structure of the wood with the color white
- ▶ slip resistance R10/DIN 51130
- ▶ DIN 53160 (Resistance to saliva and sweat)
- ▶ EN 71-3 (Child safe coating, p. 3: migration of certain elements)

TECHNICAL DATA:

Packaging:	metal container + plastic bottle
Packsize:	0,8 + 0,2 l
Shelf life:	at least 12 months
Colour:	white
Mixing ratio:	4 : 1
Consumption per coat:	approx. 25 - 50 ml/m ²
Application Climate	between 18 – 25 °C and 35 – 65 % relative humidity
Pot life:	approx. 45 minutes*
Further applications:	after approx. 10 - 30 minutes*
Load-bearing:	after approx. 24 hours*
Washable:	after approx. 24 hours*

*At 20 °C and 50 % rel. humidity

Consumption can vary according to the absorbency and condition of the surface of the wood or parquet to be impregnated.

NOTE:

The user is required to create a sample area identical to construction and work routine (including oil or lacquer) on the wood floor that will be performed to the customer. This is to get the customers approval regarding color and appearance.

SURFACE PREPARATION:

The surface to be oiled must be filled, clean, dry, free of impurities and sanded in accordance with the local standards.

IMPORTANT NOTES:

Pads or textile materials soaked in the product may spontaneously ignite on contact with air: thoroughly dampen soaked rags, pads, etc. with water and store / dispose of them in tightly sealed, fireproof containers.

Grinding dust from oxygen-drying systems is self-igniting. Fire hazard! Wet the grinding dust and dispose of it in tightly sealed, fireproof containers!

IMPORTANT NOTES:

- ▶ Optimum temperature is 18 to 25 °C and relative humidity between 35 % and 65 %. Low temperatures and high humidity will extend the drying time. High temperatures and low humidity will shorten the drying time.
- ▶ Many exotic woods such as Teak, Ipe Lapacho, smoked Oak or Wenge as well as softwoods contain ingredients (e.g. so-called inhibitors, resins or mineral storages) which can lead to significant drying delays, wetting disturbances or colour changes. Due to the variety and different qualities of these woods, the species should be established and testing carried out before coating.
- ▶ Recommended on commercially available, light-colored, European types of wood.
- ▶ Shelf life minimum 12 months in original packaging when stored in dry conditions. Protect from freezing and do not expose to temperatures over 40 °C.
- ▶ After adding the hardener do not re seal the container to avoid the risk of excessive expansion of mixed product.
- ▶ For joint sealing a suitable PALLMANN JOINT FILLER must be used.
- ▶ For boards that have visible joints or/and are bevelled, we recommend to obtain technical advice.
- ▶ The consumption on end grain wood can increase significantly (approx. 140 ml/m²). Where end grain is to be coated you should work with roller application and the drying time should be 72 hours before over-coating.
- ▶ For structured wood floors, apply/trowel up the oil at points and immediately spread it thinly and evenly with the PALLMANN CLEANING PAD BEIGE. Remove excess oil with the PALLMANN CLEANING PAD WHITE. All excess oil has to be removed from the surface.
- ▶ Light traffic of the surface is possible not earlier than 24 hours after polishing.
- ▶ Leave the freshly oiled surface at least 24 hours before covering.
- ▶ The maintenance care and cleaning should be carried out at the earliest after 24 hours.
- ▶ For long life of the flooring, we recommend regular care according to the manufacturer's instructions with PALLMANN MAGIC OIL CARE WHITE and maintenance cleaning with PALLMANN CLEAN. For the exact cleaning and care cycles, please refer to the care instructions for oiled wooden floors. For the exact cleaning and care cycles, please refer to the care instructions for oiled floors.
- ▶ Coloured, oiled wood floor surfaces are unique. Slight colour irregularities are acceptable and often unavoidable.
- ▶ Some yellowing of the timber may occur (dark yellowing).

- ▶ The following standards and notices are applicable and especially recommended: DIN 18356 "Working with parquet and woodblocks".

PROTECTION OF THE WORKPLACE AND THE ENVIRONMENT:

Solvent-free. Component A: Non-flammable but risk of spontaneous combustion (see "Important Note" below). Component B: Non-flammable. Contains pre-polymerised isocyanate. Harmful if inhaled. May cause an allergic skin reaction. May cause respiratory irritation. Both components: Provide good ventilation during and after use. Use barrier cream and protective gloves / goggles. Avoid contact with skin or contact with eyes. After contact with skin, wash immediately with plenty of water and soap. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Observe safety information on product label as well as safety data sheet.

DISPOSAL:

Where possible, collect product residues and re-use. Do not allow dispersal into drains, sewers or ground. Empty, scraped and drip-free containers are recyclable. Containers with liquid residue, as well as the liquid product, are classed as Special Waste. Dried product residues are classed as Construction Waste.